

3784 Fiberglass Cloth

Technical Data Sheet (TDS)

Style	3784
Warp Yarn	EC91361/2
Fill Yarn	EC91361/2
Weave	8H Satin
Thread Count Warp(Per inch)	45±1
Thread Count Fill(Per inch)	33±1
Basic Weight (g/m²)	901
Thickness(mm)	0.69
Tensile strength Warp(N/2.5cm)	≥2500
Tensile strength Fill(N/2.5cm)	≥2500
Loss on ignition(%)	≤1.47
Working Temperature(°C)	600

contact

E-mail: rssale651@czrsxcl.com WhatsApp: +86 18068755165